


Bondline 700

Thermal Adhesive Tape



Bondline 700 is an electrically isolating thermal adhesive tape designed to mechanically fix and thermally connect electronic devices and FR4 PCBs to a heatsink. Formulated from acrylic, **Bondline 700** is pressure sensitive and the differing thicknesses conform to varying surface textures which fills micro-air voids between contact surfaces and reduces thermal resistance. **Bondline 700** is developed for applications requiring good thermal transfer, dielectric strength and permanent adhesion.

Features

- Electrically isolating, acrylic thermal tape
- Conformability fills micro air voids between mating surfaces reducing thermal resistance
- Allows sufficient heat exchange between component and cooling mechanism

Availability

- Available in standard thicknesses of 0.15mm, 0.25mm and 0.5mm
- Supplied on 30m to 50m rolls and to specified widths on request
- Available as custom kiss-cut parts on rolls for starboards and as die-cut custom shapes

Typical Physical Properties

Property (unit)	Test Method	Bondline 700 (0.25mm)
Colour	Visual	White
Thermal Conductivity (W/mK)	ASTM D5470	1.1
Thermal Resistance (K-cm ² /W)	ASTM D5470	3
Operating Temp (°C)	In House	-25 to +130

Benefits

- Provides excellent adhesion between a variety of substrates
- Delivers a permanent mechanical bond with high dielectric strength
- Simple to handle and apply

Recommended Uses

- Mounting high and mid-power LED modules to a heatsink
- To provide a fast and consistent method of attaching power components to a heat sink

Electrical and Mechanical Information

Property (unit)	Test Method	Bondline 700 (0.25mm)
Shear Adhesion (kg/cm ²)	ASTM D-1002	3.5
Tensile Strength (Kg/cm)	ASTM 412	0.15
Breakdown Voltage (Volts AC)	ASTM D149	>6000
Elongation (%)	ASTM 412	400
Flame Rating	U L94	VO



www.universal-science.com

UK +44 (0) 1908 222 211 NL +31 (0) 35 5239 209
 IT +39 (02) 395 613 61 FR +33 (0) 1602 00276
 USA +1 440 382 1077



This material is often used in these industries:



Information furnished by Universal Science regarding technical data is believed to be accurate and reliable but our customers bear the responsibility in assessing fitness for purpose. Universal Science makes no warranties as to the fitness, merchantability or suitability of any materials or products for any uses. Universal Science shall not be liable for damages of any kind. Universal Science terms and conditions of sale apply.